


Scheda Tecnica

TESSUTI D'ORIENTE



Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Base	Silver, gold
Hardening	Physical hardening through water evaporation and coalescence of the polymer
Specific weight	1010 gr / l
VOC	40 gr / lt
Dry residue	50 % + 1
Components	1
Minimum thickness	50 - 60 microns
Estimated yield	9 m ² / kg for a thickness of 50 microns
Environmental conditions	Ambient temperature:from + 8 to 35° CHumidity:0 - 75 %Humidity of the substrate:< 10 %
Flash point	Component A > 114° C
Resistance to Temperature	max 60° C
Preparation of surfaces	The substrate must be solid and compact, otherwise it must be consolidated. New surfaces: apply a coat of acrylic insulating product « IMPRIMITURA ACRILICA ». Old surfaces: remove parts that are peeling off and after thorough cleaning apply a coat of acrylic insulating product « IMPRIMITURA ACRILICA ».
·	



Preparation of the product	Ready - to - use product. Mix the product before the use Component A 100
Application	After adequate preparation of the substrate, the product is applied: Apply one coat of white primer with a brush or roller. Once the primer is dry, apply a top coat by spreading the paint vertically in a direction. Once dry, to enhance the shantung effect, apply a second coat in the same way as the first.
Shelf life	1 year in a cool and dry place (max 40° C)
Packs	Kg 5 – Kg 2