

# ATTACCA E STACCA



Decorative product for internal spaces



Codice

0738

Description

It is a decorative paint which transforms the walls or the surfaces, where it is applied, in substrates capable of attracting and of keeping calamites or magnets. In this way, the walls become real magnetic walls, where it is possible to hang, with small magnets, photographs, sheets, notes, block notes, decorative calamites, numbers and magnetic letters so that children can play. It is a product based on acrylic resins in water dispersion and on lamellar metallic particles.

Use

It is used for the painting of interior wall surfaces. It can be applied in houses, offices, children's recreation centers, schools, relaxation areas, or in any other place where you want to create a magnetic wall. It is a decorative paint easy to use and it is applied as a normal paint

Appearance of the film

Matt

Appearance

Liquid

Color

Black

Components	1
Hardening	Physical hardening through evaporation of water
Specific weight	About 2.000 gr / ml
VOC	40 gr/ liter
pH	7.0-9.0
Estimated yield	5 m <sup>2</sup> / litre according to the absorption of the support
Flash point	> 100°C
Application	<p>Fill and prime the surfaces; on the substrates very absorbent, it is necessary to give also a priming coat.</p> <p>Apply 3 - 4 coats of paint effect magnet in order to obtain a good magnetic power; between the coats, it is necessary to spend at least 4 - 5 hours.</p> <p>Apply one or two coats of paint effect blackboard or of a good paint or of an acrylic enamel in the color that you want.</p> <p>The product should be applied as a normal paint, using the method of crossing coats.</p> <p>It can be applied both with a brush and with a roller.</p> <p>If you choose the first option, you have to use nylon or natural bristle brushes.</p> <p>If you choose the second option, you have to use rollers with rubber tops or short-haired rollers.</p>
Preparation of the product	Diluted to 10 %
Environmental conditions	<p>Ambient temperature: da + 8 a 40°C</p> <p>Temperature of the support: &gt; di 10°C</p> <p>Humidity: 0 - 80 %</p> <p>In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.</p>

### Precautions:

Shake well before and during the use in such a way as to avoid the precipitation of the metallic particles.  
Do not apply an exaggerated layer of finish because it could weaken the magnetic power of the wall.  
Do not apply on wet surfaces.  
Do not apply at temperature below 10° C.  
Do not apply when moisture is above 80 %.

### Drying and hardening time

	20°C
Dry to touch	1 hours
Dry in depth	4 hours
Crystallized	5 days

### Time of overpainting

	20°C
Minimum (hours)	4/5
Maximum	unlimited in the absence of contaminants

### Shelf life

1 year in a cool and dry place (max 40° C)

### Packs

Lt. 0,750