

DELICATO



Water - based acrylic finish

Washable

Decorative paint



Code

0711

Description

Precious decorative finish, which has a metallic sheen, based on acrylic resins in water emulsion with an excellent resistance to washing and a high flexibility in application and dilatation, for internal spaces.

Use

It can be applied to wall surfaces, properly prepared with concrete, where a luminescent aesthetic appearance combined with excellent resistance to washing with cleansing agents are required.

Appearance of the film

Metallic

Color

Color chart

Component

1

Hardening

Physical hardening through evaporation of water and union of the polymer

Specific weight

From 1,03 gr/m

VOC	40 gr/ liter					
Minimum thickness	50 -60 micron					
Estimated yield	4-5 m ² / kg for a thickness of 50 microns					
Flash point	Component A	> 114°C				
Temperature resistance	Max 60° C					
Preparation of surfaces	<p>New surfaces: Apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water).</p> <p>Old surfaces: Remove any parts that are peeling off and, after a careful cleaning of the substrate, apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water).</p>					
Preparation of the product	<p>It is ready to use. Mix the product before the use.</p> <table><tr><td>Component A</td><td>100</td></tr></table>				Component A	100
Component A	100					
Environmental conditions	<p>Ambient temperature: from + 5 to 40° C</p> <p>Temperature of the support: > 10° C</p> <p>Humidity: 0 - 85 %</p> <p>In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.</p>					
Drying and hardening time	For the thickness of 50 microns	10° C	20° C	30° C		
	Dry to touch	3	1	0,5 hours		
	Dry in depth	8	4 - 5	2 hours		

Time of overpainting

Minimum (hours)	10° C	20° C	30° C
	8	4	3 hours
Maximum	unlimited in the absence of contaminants		

Application

After an appropriate preparation of the substrate, apply the product as follows: apply a coat of our white primer « SABBIAFOND » with brushes or roller diluted with water to 20 - 25 %. In order to obtain a color of our chart, mix in the amount shown on our chart LINEA PLATINUM of our paste TONER.
First coat: apply « DELICATO », not diluted, with a brush. On the surface, the brush strokes must be crossed avoiding painting the same position in the same way.
Second coat: after 6 hours, apply a second coat, in the same way, in order to obtain wonderful contrasts of light.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Kg. 2 - Kg. 5.